



**WENDOVER GRANULAR  
MURIATE OF POTASH  
(SGN=260)**

CHEMICAL DATA	RANGE	TYPICAL	GUARANTEE
K <sub>2</sub> O%	60.0 - 61.0	60.5	60.0 min.
Moisture %	0.10 - 0.30	0.17	

PHYSICAL DATA			
U.S. MESH	OPENING MM	RANGE % CUMULATIVE	TYPICAL % CUMULATIVE
+6	3.35	15 - 40	20
+8	2.36	55 - 75	60
+10	1.70	80 - 90	85
+14	1.18	95 - 99	97
+20	0.85	97 - 100	98

TYPICAL CHEMICAL ANALYSIS	
KCl	95.70
K	50.2
Mg	0.09
Ca	0.07
NaCl	2.8
Cl	47.2
SO <sub>4</sub>	0.3
Insol.	0.05

TYPICAL BULK DENSITY
70 - 72 LBS/ft <sup>3</sup>

Angle of Repose = 32 degrees

The information contained in this data sheet is believed to be a true and accurate representation of the average properties obtained from commercial production lots and should not be considered a guaranteed specification. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control.