



**METAL RECOVER SALTS
WENDOVER**

**KCl - NaCl
20 - 50%
50 - 80%**

PHYSICAL DATA			
U.S. MESH	OPENING MM	RANGE	TYPICAL
+4	4.75	1 - 5	3
+6	3.35	6 - 15	12
+8	2.36	15 - 27	25
+10	2.00	28 - 35	30
+14	1.40	35 - 50	45
+20	0.85	50 - 80	62
Pan		100	100

TYPICAL CHEMICAL ANALYSIS	
KCl	20 - 50
NaCl	50 - 80
Mg	0.70
Ca	0.15
Moisture	0.20
SO ₄	1.2
Insol.	0.10

TYPICAL BULK DENSITY
66 - 74 LBS/FT ³ (1057 - 1185 KG/M ³) Angle of Repose = 30 - 34 degrees

The information contained in this data sheet is believed to be a true and accurate representation of the average properties obtained from commercial production lots and should not be considered a guaranteed specification. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control