

INTREPID: Trio

Fine Standard TRIO®



| PROPERTY | RANGE | TYPICAL | GUARANTEE |
|------------------|------------|---------|------------|
| K | 17.8-18.3% | 18.0% | 17.8% min. |
| K ₂ O | 21.5-22.0% | 21.7% | 21.5% min. |
| Mg | 10.8-11.2% | 11.0% | 10.8% min. |
| MgO | 17.9-18.6% | 18.2% | 17.9% min. |
| S | 22.0-22.4% | 22.2% | 22.0% min. |
| SO ₄ | 66.0-67.2% | 66.6% | 66.0% min. |
| Chloride | | 2.0% | |
| Moisture | 0.1 - 0.5% | 0.35% | |
| SGN | 30-50 | 40 | |
| UI | | 15 | |
| | | | |

PARTICLE SIZE DISTRIBUTION

TYPICAL CHEMICAL ANALYSIS %

18.2

0.5 2.0

0.7

7

Κ

Са

Na

рΗ

Insoluble

| TYLER MESH | OPENING MM | TYPICAL % CUMULATIVE |
|------------|------------|-------------------------|
| +20 | 0.85 | 5 |
| +28 | 0.6 | 25 |
| +35 | 0.425 | 50 |
| +48 | 0.3 | 70 |
| +65 | 0.212 | 80 |
| | | |

TYPICAL BULK DENSITY

93 lbs/ft³ 1490 kg/m³

TYPICAL ANGLE OF REPOSE

34-37 degrees



East Plant

210 Red Cloud Road Carlsbad, New Mexico 88220

575.234.3872 :: Direct to Plant 800.451.2888 :: Customer Service



The information shown in this data sheet represents average properties of product analyses of composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values due to natural variability within the product. Additional handling, transportation, or improper/extended storage may affect product analyses. Intrepid Potash disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product. **Revision Date :: 1/9/18**

INTREPID 1001 17th Street, Suite 1050, Denver, CO 80202 www.intrepidpotash.com



