





PROPERTY	RANGE	TYPICAL	GUARANTEE
K ₂ O	60.0-61.0%	60.5%	60.0% min.
Moisture	0.1-0.3%	0.10%	
SGN	215 - 245	230	
UI		45	

PARTICLE SIZE DISTRIBUTION


TYLER MESH	OPENING MM	TYPICAL% CUMULATIVE
+6	3.330	2
+8	2.360	48
+10	1.650	92
+14	1.170	99.4
+20	0.833	99.8

TYPICAL BULK DENSITY

63 lbs/ft³ 1010 kg/m³

TYPICAL ANGLE OF REPOSE

28-32 degrees



TYPICAL CHEMICAL ANALYSIS %				
KCI	95.7			
K	50.2			
Mg	0.02			
Ca	0.5			
Na	1.0			
Cl	47.0			
NaCl	2.6			
SO ₄	0.9			
Insoluble	0.06			





INTREPID





