



## **Feed Grade** Standard Potash 62% K<sub>2</sub>O



PROPERTY	RANGE	TYPICAL	GUARANTEE
K <sub>2</sub> O	62.0 - 62.5%	62.3%	62.0% min.
Moisture	0.1 - 0.5%	0.20%	
SGN	30-60	45	

## PARTICLE SIZE DISTRIBUTION

TYLER MESH	OPENING MM	TYPICAL % CUMULATIVE
+10	1.68	1
+14	1.18	2
+20	0.85	10
+28	0.6	30
+35	0.425	55
+48	0.3	70
+65	0.212	85
+100	0.15	95
-100	< 0.15	5

TYLER MESH	OPENING MM	TYPICAL % CUMULATIVE
+10	1.68	1
+14	1.18	2
+20	0.85	10
+28	0.6	30
+35	0.425	55
+48	0.3	70
+65	0.212	85
+100	0.15	95
-100	< 0.15	5

THE TORKE ELEMENT THE THE THE TORK		
As	<0.3 ppm	
Ве	<0.01 ppm	
Bi	<0.05 ppm	
Br	0.03%	
Cd	<0.05 ppm	
Cr	<0.1 ppm	
Cu	<1 ppm	
Fe	<20 ppm	
Hg	<5 ppb	
Na	0.75%	
Ni	<0.1 ppm	
Pb	<1 ppm	
Zn	<3 ppm	

TYPICAL BULK DENSITY

TYPICAL ANGLE OF REPOSE

**TYPICAL ELEMENTAL ANALYSIS** 

82 lbs/ft<sup>3</sup> 1310 kg/m³

32 degrees

# **North Plant**

484 State Highway 243 Carlsbad, New Mexico 88220

575.234.3872 :: Direct to Plant 800.451.2888 :: Customer Service



### **TYPICAL CHEMICAL ANALYSIS %**

KCI	98.6
K	51.7
Mg	0.07
Ca	0.1
NaCl	0.8
Cl	45.1
SO <sub>4</sub>	0.2
Insoluble	0.2



The information shown in this data sheet represents average properties of product analyses of composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values due to natural variability within the product. Additional handling, transportation, or improper/extended storage may affect product analyses. Intrepid Potash disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product. Revision Date :: 4/11/22

707 17th Street, Suite 4200, Denver, CO 80202 www.intrepidpotash.com



